Bodycote warringtonfire Holmesfield Road Warrington WA1 2DS

Tel: (01925) 655116 Fax (01925) 646672 WARRES No:

180407

TEST:

Indicative

DATE:

24th February 2008

## SURFACE SPREAD OF FLAME TEST – BS 476: PART 7: 1997 LABORATORY RECORD SHEET

CLIENT:

**OBSERVERS:** 

Mr P King

MATERIAL DESCRIPTION:

Nominally 48mm thick recycled plastic sheet material

**FACE TESTED:** 

One

**MODIFIED SPECIMENS:** 

**REDUCED SPECIMENS:** 

Clients Reference				H														
Specimen No. 1		1	2 mm		3 mm		4 rmm		5 mm		6 mm		7 mm		8 mm		9 mm	
Travel at 1½ mins	180mm																	
Time to Travel	min	sec	min	sec	min	sec	min	sec	min	sec	min	sec	min	sec	min	sec	min	sec
75mm	0	39																
165mm	1	17																
190mm	1	32						-										
215mm	1	48																
240mm	2	01																
265mm	2	13																
290mm	2	33																
375mm	3	40																
455mm	5	37																
500mm	6	52																
525mm	7	58																
600mm																		
675mm																		
710mm																		
750mm																		
785mm																		
825mm																		
Time to Final Travel	10	00																
Final Travel	550mm		mm		mm		mm		mm		mm		mm		mm		mm	

Softening/ delamination?

NONE

More than 6 specimens Tested --

Any supplementary

YES

observations? Designation Class

NOT APPLICABLE

Tested By:

P CADE

<sup>\*</sup>Indicative tests are normally performed in the same way as formal tests but on a reduced number of specimens. They are conducted only for the purposes of the sponsor of the test, mainly for research and development purposes. The full conditions of the Standard will not be complied with in terms of number of specimens tested, specimen construction and/or conditioning requirements. Indicative test results should not be accepted as a substitute for formal test results obtained in accordance with the requirements of the standard.